

Biresin® G38 Heat-resistant EP Casting resin, filled

Areas of Application

- Manufacture of heat resistant moulds, e. g. vacuumforming moulds
- Casting of heat resistant backfillings of foundry patterns
- Casting of heat resistant mouldings

Product Benefits

- Good flowability and good degassing
- Casting thickness up to 40 mm
- Demoulding without heat treatment
- Only low shrinkage
- Good mechanical properties, at elevated temperatures too
- Increasing of good mechanical properties after post curing
- Cured mouldings mechanically workable

Description

- Basis Two component epoxy system
- Component A **Biresin® G38**, epoxy resin, grey
- Component B **Biresin® G38**, amine, amber

Processing Data		Component A	Component B
Individual components		Biresin® G38	Biresin® G38
Viscosity, 25°C	mPa.s	~ 40.000	~ 200
Density	g/ml	1.86	0.96
Mixing ratio A : B	in parts by weight	100	7
		Mixture	
Mixed viscosity, 25°C	mPa.s	~ 11.000	
Potlife, 500 g, RT	min	120	
Demoulding time, RT, without post curing	h	16 - 24	

Physical Data (approx. values)

Biresin® G38 (A)		with component B	Biresin® G38	
Curing conditions	time	temperature	14 d RT	4 h + 2 h 60°C 100°C
Density	ISO 1183	g/cm³	1.8	
Shore hardness	ISO 868	-	D 88	D 90
Flexural strength	ISO 178	MPa	51	68
Compressive strength	ISO 604	MPa	94	112
Impact resistance	ISO 179	kJ/m²	5	8
Heat distortion temperature	ISO 75B	°C	54	> 130
Linear shrinkage	internal	%	0.08	
CTE value, α_T	DIN 53 752	K ⁻¹		35-40 x 10 ⁻⁶

Packaging

Individual components	Biresin® G38 (A) Biresin® G38 (B)	10 kg; 5 kg net 6 x 0.7 kg net in a box
-----------------------	--	--

Processing

- The material, processing and mould temperature must be from 18 to 25°C.
- The A component must be mixed thoroughly before use.
- Take care that resin and hardener are mixed thoroughly without air entrapment.
- The resin mix can be poured, beginning at the lowest point into previously released moulds (e. g. with Sika® Trennmittel 810, 815 Quick resp. Sika® Trennwachs 818, for more information see Product Data Sheet).
- For cleaning of cured mouldings from wax residues we recommend Sika® Reinigungsmittel 5. Before application of other cleaners test their compatibility with resin.

Storage

- Minimum shelf life of Biresin® G38 resin (A) is 18 month and of Biresin® G38 hardener (B) 24 month under room condition (18 - 25°C), when stored in original un-opened containers.
- After prolonged storage at low temperature, crystallisation of components may occur. This is easily removed by warming up for a sufficient time to a maximum of 70°C. Allow to cool to room temperature before use.
- Containers must be closed tightly immediately after use to prevent moisture ingress. The residual material needs to be used up as soon as possible.

Health and Safety Information

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety related data.

Disposal considerations

Product Recommendations: Must be disposed of in a special waste disposal unit in accordance with the corresponding regulations.

Packaging Recommendations: Completely emptied packagings can be given for recycling. Packaging that cannot be cleaned should be disposed of as product waste.

Value Bases

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

Legal Notice

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Further information available at:

Sika Deutschland GmbH

Subsidiary Bad Urach

Stuttgarter Str. 139

D - 72574 Bad Urach

Germany

Tel: +49 (0) 7125 940 492

Fax: +49 (0) 7125 940 401

Email: tooling@de.sika.com

Internet: www.sika.com

