

DESCRIPTION

Glass clear epoxy resin for art and decoration applications.

PROPERTIES

- Easy to use
- Ratio mixing by volume 2/1
- High transparency
- Can be applied on any material (wood, ceramic, plastic, paper)
- Thickness coating 1 to 3 mm
- Doming effect

| PHYSICAL PROPERTIES | | | | |
|---|-----------------|------------------|-------------|-------------|
| Composition | | RESIN | HARDENER | MIXED |
| Mix ratio by weight | | 100 | 43 | |
| Mix ratio by volume at 25°C | | 100 | 50 | |
| Aspect | | liquid | liquid | liquid |
| Colour | | transparent blue | transparent | transparent |
| Viscosity at 25°C (mPa.s) | BROOKFIELD LVT | 2,600 | 800 | 1,500 |
| Specific gravity at 25°C (g/cm ³) | ISO 1675 : 1985 | 1.17 | 1.00 | - |
| Specific gravity of cured product at 23°C | ISO 2781 : 1996 | - | - | 1.15 |
| Pot life at 25°C on 143 g (min) | Gel Timer TECAM | | | 42 |
| Tackfree time in thin layer (1 to 3 mm) at 20°C | | - | h | 4 - 5 |

| MECHANICAL PROPERTIES at 23°C (1) | | | |
|--|------------------|--------------|---------|
| Glass transition temperature (T _g) | ISO 11359 : 2002 | °C | 64 |
| Hardness | ISO 868 : 2003 | Shore D1/D15 | 87 / 85 |

(1): Average values obtained on standard specimens / Hardening 16 hours at 80°C

PROCESSING CONDITIONS

Mixing by hand. Bubbles created can be broken by using a flame or by brushing the surface with forced hot air.

Before handling, we recommend to let dry 7-8 hours at room temperature.



BUILDING TRUST



TRANSLUX D 155-1

HIGH GLOSS WATERCLEAR SURFACE COATING
EPOXY RESIN

HARDNESS 87 SHORE D

HANDLING PRECAUTIONS

Normal health and safety precautions should be observed when handling these products :

- Ensure good ventilation,
- Wear gloves, safety glasses and waterproof clothes.

For further information, please consult the product safety data sheet.

STORAGE CONDITIONS

Shelf life of this product is 12 months stored in a dry place and in original unopened containers at a temperature between 15 and 25° C.

PACKAGING

| TRANSLUX D 155-1 RESIN | TRANSLUX D 155-1 HARDENER |
|------------------------|---------------------------|
| 227 kg | 200 kg |
| 5 kg | 2.15 kg |

GUARANTEE

The information of our technical data sheet are based on our present knowledge and the result of tests conducted under precise conditions. It is the responsibility of the user to determine the suitability of AXSON products, under their own conditions before commencing with the proposed application. AXSON refuse any guarantee about the compatibility of a product with any particular application. AXSON disclaim all responsibility for damage from any incident which results from the use of these products. The guarantee conditions are regulated by our general sale conditions.

AXSON FRANCE - SikaAxson
Head Office France
 +33 1 34 40 34 60
axson@axson.com
www.sikaaxson.com

GERMANY
 +49 (0)7125 940 492
tooling@de.sika.com
www.sikaaxson.de

ITALY
 +39 02 96 70 23 36
axson@axson.it
 axson.it

SPAIN & PORTUGAL
 +34 93 225 16 20
axson@axson.es
 axson.es

U.K.
 +44 1 638 66 00 62
sales@axson.co.uk
 axson.com

SLOVAKIA
 +421 37 642 25 26
office@axson-ce.sk
 axson-ce.sk

NORTH AMERICA
 +1 517 663 8191
info@axsontech.us
 axsontech.us

MEXICO
 +52 55 52 64 49 22
axson@prodigy.net.mx
 axson.com.mx

JAPAN
 +81 564 26 25 91
sales@axson.jp
 axson.jp

CHINA
 +86 21 58 68 30 37
china@axson.cn
 axson.cn

INDIA
 +91 20 25560710
info.india@axson.com
 axson.com

MIDDLE EAST
 +971 7 2432227
info.middleeast@axson.com
 axson.com